



Testing Conditions

Items	Depth of Discharge	Light Load (2.1% DOD)	Heavy Load (50% DOD)	Deep Cycle 75% DOD
Specifications		SAE J240, JIS D 5301	JIS D 5301	SBA(S0802)
Discharge 放電		4min*25A	40A*1HR	20A*3HR
Charging 充電		10min*14.8V(max.25A)	10A*5HR	20A*3.6HR
Charging Volume (% of discharged Capacity) 充電量 (対放電量)		-	125%	120%
Ambient Temperature 周囲の温度		40±3℃	40±3℃	40±3℃
The End of Service Life 寿命 (What percentage is reached when the capacity falls below of its original value) (放電量がそれぞれの値に減少したときを寿命とする)		-	(50%)	(60%)